IMPERGUARD
Waterproofing solutions

IG1015
ACRYLIC PRIMER — BLEED BLOCKER

PRODUCT DESCRIPTION
The IG1015 is a water-based acrylic polymer emulsion resin with multiple uses: an asphalt-bleed-blocking primer under silicone coatings, and a saturant that embeds and adheres polyester fabrics in reinforced, fluid-applied roof membranes. It may be used on EPDM, PVC, Hypalon, concrete, modified bitumen and asphalt BUR roofs, and as a base coat for concrete, unparged CMU masonry and EIFS walls before a silicone finish coat. Its light-yellow color turns amber as it dries, giving a visual confirmation of the cure level before the topcoat is applied.

COMPOSITION
Water-based acrylic polymer emulsion resin.

APPLICATION
- Mechanically mix before use.
- Power wash the surface clean with IG0115; it must be clean and dry before application.
- Apply when the air temperature is at least 5 °C (40 °F) and rising, humidity is below 90% and no rain is expected for 48 hours; keep the surface below 38 °C (100 °F) to avoid premature curing.
- Apply with a soft-bristle roller, brush or spray equipment.
- Avoid water-retaining areas: on surfaces that hold water for more than 48 hours, service life is greatly reduced and loss of adhesion is to be expected.
- As a bleed-blocking primer under silicone: 1 to 1.5 gal/100 sq. ft. (1.5 gal/100 sq. ft. on granulated modified bitumen; more on cracked or irregular surfaces). On asphalt and bitumen, it blocks the oils that would otherwise bleed through and discolor the silicone coating (without primer, discoloration is to be expected). Allow to dry 24–48 hours before applying IG8000.
- As an adhesion promoter: may be required on aged PVC, before the silicone coating.
- TPO roofs: use a special TPO primer (the IG1015 is not intended for TPO).
- As a polyester-fabric saturant (reinforced membrane): 3 gal/100 sq. ft.

CLEAN UP
Clean tools and equipment with soap and water while the product is still wet.

STORAGE
Store between 10 °C and 35 °C (50 °F–95 °F). Keep from freezing (water-based product). Keep out of direct sunlight. Do not heat or thin. (High temperatures and humidity during storage may shorten shelf life.)

SHELF LIFE
Two years from the date of manufacture.

CAUTIONS
- For professional use only. For exterior use only; do not use indoors.
- May irritate skin and eyes; wear gloves and eye protection, and avoid prolonged inhalation of fumes.
- Do not ingest. If swallowed, do not induce vomiting and contact a health professional immediately. Poison Centre — Canada: 1-844-764-7669; Québec: 1-800-463-5060.
- In case of a spill, contact CANUTEC: 1-888-226-8832 (or *666 on a cell phone).
- Consult the Safety Data Sheet (SDS) and WHMIS label before use.

114, 2e Avenue, Portneuf QC G0A 2Y0 418-285-0090 **imperguard.com**

IG1015 ACRYLIC PRIMER — BLEED BLOCKER

SPECIFICATIONS

Color: yellow (turns amber as it dries)

PROPERTY	TEST METHOD	VALUE
Viscosity	ASTM D2196	110,000 cP
Solids by weight	ASTM D1644	62%
Solids by volume	ASTM D2697	45%
Weight per gallon	ASTM D1475	11.1 lb
Tensile strength	ASTM D2370	250 psi
Elongation	ASTM D2370	250%
Flash point	ASTM D56	N/A
VOC content	EPA 24	< 50 g/L
Container sizes	–	5 gal

LIMITED WARRANTY

To the extent permitted by local law, except as set forth below, the seller makes no warranty of merchantability or fitness for a particular purpose with respect to the goods sold herein. No other warranty, express or implied, is granted beyond the terms set forth in this document. The seller warrants that this product is free of material or manufacturing defects under normal use for one year from the date of purchase. This warranty does not cover defects or failures resulting from misuse or incorrect application.

LIMITATION OF LIABILITY

In the event of a defect, the buyer's sole remedy shall be a refund of the purchase price or replacement of the defective material, at the seller's option. Under no circumstances shall the seller be liable for any direct, indirect, special, incidental or consequential damages, whether based on contract, tort (including negligence) or any other legal theory.



114, 2e Avenue, Portneuf QC G0A 2Y0 418-285-0090 imperguard.com